



FX MINERALS, INC.

257 Kennedy Park Marina Road

Newell, WV 26050

Tel: 304 387-1160

Fax: 304 387-2205

Brown Fused Alumina

PRODUCT DATA

Property	Specification	Typical
Al ₂ O ₃	94.5% min.	95.3%
TiO ₂	3.00% max.	2.10%
Fe ₂ O ₃	0.30% max.	0.13%
SiO ₂	1.50% max.	1.30%
K ₂ O + Na ₂ O	0.25% max	0.11%
CaO + MgO	0.60% max.	0.41%

Bulk Density (As 3x6 mesh)	3.85 g/cc min.	3.90 g/cc
Magnetics	1000 ppm max.	
Moisture	0.5% max	<0.1%

Various Sizes and Packaging Options Available

Information on this data sheet for general use only and specific situations may apply to all products.
This sheet is property of FX Minerals, Inc. and shall not be used, copied or released without
permission from FX Minerals, Inc.