



## FX MINERALS, INC.

257 Kennedy Park Marina Road

Newell, WV 26050

Tel: 304 387-1160

Fax: 304 387-2205

### Rotary Bauxite RK 82

---

#### PRODUCT DATA

Property	Specification	Typical
Al <sub>2</sub> O <sub>3</sub>	82.0 % min.	82.3%
TiO <sub>2</sub>	4.00 % max.	3.70 %
Fe <sub>2</sub> O <sub>3</sub>	2.00 % max.	1.90 %
CaO + MgO	0.70 % max.	0.60 %
K <sub>2</sub> O + Na <sub>2</sub> O	0.40 % max.	0.35 %

  

Bulk Density As 3x6 mesh	3.05 g/cc min.	3.10 g/cc min.
-----------------------------	----------------	----------------

Information on this data sheet for general use only and specific situations may apply to all products.  
This sheet is property of FX Minerals, Inc. and shall not be used, copied or released without  
permission from FX Minerals, Inc.