



# FX MINERALS, INC.

257 Kennedy Park Marina Road

Newell, WV 26050

Tel: 304 387-1160

Fax: 304 387-2205

## Rotary Bauxite RK88 CBM

Ceramic Ball Milled

### PRODUCT DATA

Rotary Kiln Bauxite RK88 is produced from the highest quality refractory grade bauxite in the world having high alumina content and low alkalis. Fine mesh sizes are produced in a ceramic lined ball mill to insure low level of iron.

Property	Specification	Typical
Al <sub>2</sub> O <sub>3</sub>	87.00% min.	87.8 %
TiO <sub>2</sub>	4.00% max.	3.6 %
Fe <sub>2</sub> O <sub>3</sub>	2.00% max.	1.5 %
SiO <sub>2</sub>	7.50% max.	5.3%
CaO + MgO	0.65% max.	0.43%
K <sub>2</sub> O + Na <sub>2</sub> O	0.35% max.	0.24%

Bulk Density	3.25 g/cc min.	3.27 g/cc
Sizes (Others available)		-48 mesh -100 mesh -200 mesh -325mesh

Information on this data sheet for general use only and specific situations may apply to all products. This sheet is property of FX Minerals, Inc. and shall not be used, copied or released without permission of FX Minerals, Inc.